

Modified Polymer

Product Code	NVC (%)	Solvent	Max. acid value	Typical viscosity @ 25°C (poise)	Type	Features/ application(s)
Polythane (PT-thane [®]) – urethane modified						
UA600	55	White Spirit	3	20	Linoleic	For use in floor varnishes, wood sealers and decorative paints.
UA602	100	-	5	Plastic solid	Linoleic	Good wetting properties. Suitable for oil stain formulation. Suitable for exterior wood stain application.
UA 608	55	White Spirit	3	20	Linoleic	Fast dry, excellent hardness and abrasion resistance. Suitable for floor varnishes and other wood and decorative paint.
Polysil [®] (PT-sil [®]) - silicone modified resins						
SC709	60	White Spirit	10	4	Silicone modified alkyd	Designed for high build, high durability decorative maintenance and marine finishes e.g. yacht enamels. Also suitable for rapid high temperature curing condition e.g. In-situ piping coating application.
SC707	60	White Spirit	10	4	Silicone modified alkyd	Fast true dry with good hardness development. Suitable for high build, durable decorative maintenance and marine finishes.